

Träindustri / Skumplast limningar

Abra Adhesives

TYP AV LIMNING	PRODUKT Smältlim	PRODUKT Vattenbaserat
Limning skum/skum	D740 New D2974 D2513	PF2916 PF2917 PF2951/9901 PF2920
Limning skum/textil	W450/UV D740 New D2283	PF2916 PF2917 PF2951/9901
Limning skum/trä & metall	D2974 D2513 W746LV D2504	PF2916 PF2917 PF2951/9901
Limning skum/skum omvik	D740 New W450/UV D2513	PF2916 PF2917



Träindustri / Slumplast limningar

ABRA Import Adhesives

Lim	Typ	Viskositet	Öppen tid Sekunder	R&B °C
D2283	APAO	2 200@160°C	150	98
D2504	SIS	4 700@177°C	180/PS	75
D2513	APAO	6 000@160°C	260	83
D2974	SIS	1 500@160°C	Lång/PS	82
D740 New	APAO	4 100@160°C	180	85
W450/UV	APAO	4 400@160°C	240	89
W746 LV	SIS	4 500@160°C	Lång/PS	78
PF2916	Modifierat polychloropren	3 500-4 500 mPas	Ca 20 min	-
PF2917	Naturlatex	3 000 mPas	Ca 24 tim	-
PF2920	Polychloropren 1k	1 000 mPas	Ca 20 min	-
PF2951/9901	Polychloropren 2k	250-500 mPas	Ca 90 min	-

