

Filter produktion

ABRA Import Adhesives

FILTER	PRODUKT
VECKFILTER	Abramelt F2743 Abramelt F2603 Abramelt F2618
KASSETT FILTER	Abramelt 125 Abramelt 120 Abramelt D2586 Abramelt 145D Abramelt 145F
PÅSFILTER	Abramelt C34 Abramelt C2285 Abramelt C2409 Abramelt C2310 Abramelt C2700
ÖVRIGT	Abraflex 545.4 Polyol Abramelt 145F Abramelt E2323 LV



Filter produktion

ABRA Import Adhesives

Lim	Typ	Viskositet	Öppen tid Sekunder	R&B °C
145D	APAO	2 700@180°C	60	145
145F	APAO	2 500@180°C	60	145
AM120	APAO	8 000@180°C	30-45	120
AM125	APAO	3 000@180°C	15-20	125
C2285	EVA	1 400@160°C	2	110
C2310	EVA	1 000@160°C	4-6	83
C2409	EVA	350@160°C	11-12	72
C2700	POP	1 000@160°C	3-4	106
C34	EVA	1 300@160°C	9-10	110
D2586	APAO/SIS	4 000@160°C	45	100
E2323 LV	SIS	22 000@170°C	PSA	122
F2603		6 500@160°C	2	112
F2618		1 600@160°C	6-7	73
F2743		6 000@160°C	1-2	115
545.4	POLYOL			

